


excellence in craftsmanship and performance since 1920



rainbuster 6300

material	100% woven polyolefin
tensile strength	210/180 lbs
weight	6.3 oz
tear strength	70/70 lbs
hydrostatic resistance	370 psi
accelerated UV weathering	80% strength after 2000 hrs
coating	1.75 mil average



white/silver

black/silver

† 773-927-4120
f 773-650-6046

info@puttermanathletics.com
www.puttermanathletics.com
toll-free 800-621-0146

4834 s oakley ave
chicago, il 60609